

★TOKE

W04

98-486011/42

★JP 10208279-A

Diffraction optical element manufacturing method for optical pick-up head apparatus - involves forming diffraction optical element by injection moulding using mould formed from resist pattern left in groove by non-electrolytic plating

TOSI IIBA KK 97.01.21 97JP-008865

T03 (98.08.07) G11B 7/135, 11/10

The method involves coating resist on a substrate (11) and forming a resist pattern of predetermined shape. Then, etching of the substrate is performed using the resist pattern as a mask. A heavy metal film (13) is formed on the etched substrate to form a groove on it.


A mould die (17) formed from the resist pattern left in the groove by non-electrolytic plating, after radiating X-rays onto the groove at predetermined projection angle. A diffraction optical element is formed using the formed mould by injection moulding.

ADVANTAGE - Offers inexpensive optical pick-up head apparatus. Improves optical utilization efficiency. (5pp Dwg.No.2/5)

N98-379555

W04-C02B W04-D

BEST AVAILABLE COPY



BEST AVAILABLE COPY